

→ の矢印は藤関生コンの使用配合の期間

普通ポルトランドセメント
構造体強度補正值 mS_n の適用期間
(気温の測定期間 = 1991～2020)
2024年4月版
柏崎地区生コンクリート協同組合

	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	31
1月	4.0	3.9	3.8	3.8	3.7	3.6	3.5	3.4	3.2	3.1	3.0	2.9	2.9	2.8	2.7	2.7	2.7	2.6	2.6	2.6	2.6	2.6	2.6	2.5	2.5	2.5	2.5	2.5	2.5	2.4	2.4
	3.0	2.9	2.9	2.8	2.8	2.7	2.7	2.7	2.6	2.6	2.6	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.6	2.6	2.6	2.6	2.6	2.7	2.7	2.8	2.8	2.8
2月	2.4	2.4	2.4	2.4	2.4	2.4	2.4	2.4	2.5	2.5	2.6	2.6	2.7	2.7	2.8	2.9	2.9	3.0	3.1	3.2	3.2	3.3	3.4	3.5	3.6	3.6	3.7	3.8	3.9		
	2.9	2.9	3.0	3.1	3.1	3.2	3.2	3.3	3.4	3.5	3.5	3.6	3.7	3.8	3.9	3.9	4.0	4.1	4.2	4.3	4.4	4.5	4.6	4.7	4.8	4.9	5.1	5.2	5.3		
3月	3.9	4.0	4.1	4.2	4.3	4.3	4.4	4.5	4.6	4.8	4.9	5.0	5.1	5.3	5.4	5.6	5.7	5.8	6.0	6.1	6.2	6.3	6.4	6.6	6.7	6.8	7.0	7.1	7.3	7.5	7.7
	5.4	5.5	5.6	5.8	5.9	6.0	6.2	6.3	6.5	6.6	6.8	6.9	7.1	7.3	7.4	7.6	7.8	7.9	8.1	8.3	8.5	8.7	8.8	9.0	9.2	9.4	9.6	9.8	10.0	10.2	10.4
4月	7.9	8.1	8.3	8.5	8.7	8.9	9.1	9.3	9.5	9.7	9.9	10.1	10.3	10.5	10.7	10.9	11.1	11.3	11.5	11.7	11.8	12.0	12.2	12.4	12.6	12.8	13.0	13.2	13.4	13.6	
	10.6	10.8	11.0	11.2	11.4	11.6	11.8	11.9	12.1	12.3	12.5	12.7	12.9	13.0	13.2	13.4	13.6	13.7	13.9	14.0	14.2	14.4	14.5	14.7	14.9	15.0	15.2	15.4	15.5	15.7	
5月	13.8	14.0	14.2	14.4	14.5	14.6	14.7	14.9	15.0	15.1	15.2	15.3	15.5	15.6	15.8	15.9	16.1	16.3	16.5	16.6	16.8	17.0	17.1	17.3	17.4	17.5	17.7	17.8	17.9	18.1	18.2
	15.8	16.0	16.1	16.2	16.4	16.5	16.7	16.8	17.0	17.1	17.2	17.4	17.5	17.7	17.8	18.0	18.1	18.3	18.4	18.5	18.7	18.8	18.9	19.0	19.2	19.3	19.4	19.5	19.7	19.8	19.9
6月	17.6	18.1	18.4	19.3	19.1	18.8	19.6	20.2	19.8	19.6	20.2	20.5	20.0	20.2	20.3	20.1	20.4	20.6	20.5	21.2	21.4	21.1	20.7	20.9	20.8	21.2	22.4	22.1	22.3	22.9	
	20.1	20.2	20.3	20.5	20.6	20.7	20.9	21.0	21.1	21.3	21.4	21.5	21.7	21.8	21.9	22.1	22.2	22.3	22.5	22.6	22.7	22.9	23.0	23.2	23.3	23.4	23.6	23.7	23.8	24.0	
7月	22.4	22.5	22.6	22.8	22.9	23.0	23.1	23.3	23.4	23.5	23.6	23.7	23.8	24.0	24.1	24.2	24.4	24.5	24.7	24.8	25.0	25.1	25.3	25.4	25.5	25.7	25.8	25.9	26.0	26.1	26.2
	24.1	24.2	24.4	24.5	24.6	24.7	24.9	25.0	25.1	25.2	25.3	25.4	25.5	25.5	25.6	25.7	25.8	25.8	25.9	25.9	25.9	25.9	26.0	26.0	26.0	26.0	25.9	25.9	25.9	25.9	25.8
8月	26.2	26.3	26.3	26.3	26.3	26.3	26.3	26.2	26.2	26.1	26.1	26.0	26.0	25.9	25.9	25.8	25.7	25.6	25.6	25.5	25.4	25.3	25.2	25.1	25.0	24.9	24.8	24.7	24.6	24.5	24.4
	25.8	25.7	25.6	25.6	25.5	25.4	25.3	25.3	25.2	25.1	25.0	24.9	24.8	24.7	24.6	24.4	24.3	24.2	24.0	23.9	23.8	23.6	23.5	23.3	23.1	23.0	22.8	22.6	22.5	22.3	22.1
9月	24.3	24.2	24.1	23.9	23.8	23.6	23.5	23.3	23.1	22.9	22.7	22.5	22.3	22.1	21.9	21.7	21.5	21.2	21.0	20.8	20.6	20.4	20.1	19.9	19.8	19.6	19.4	19.2	19.1	18.9	
	21.9	21.7	21.5	21.3	21.2	21.0	20.8	20.6	20.4	20.2	20.0	19.8	19.6	19.4	19.2	19.0	18.8	18.6	18.5	18.3	18.1	17.9	17.7	17.5	17.3	17.1	16.9	16.7	16.5	16.4	
10月	18.7	18.6	18.4	18.3	18.1	17.9	17.7	17.5	17.3	17.1	16.9	16.7	16.5	16.3	16.0	15.8	15.6	15.4	15.2	15.0	14.8	14.7	14.5	14.3	14.1	13.9	13.7	13.5	13.3	13.1	13.0
	16.2	16.0	15.8	15.6	15.4	15.2	15.0	14.8	14.6	14.4	14.2	14.0	13.9	13.7	13.5	13.3	13.1	12.9	12.7	12.6	12.4	12.2	12.0	11.8	11.6	11.4	11.3	11.1	10.9	10.7	10.6
11月	12.8	12.6	12.4	12.3	12.1	12.0	11.8	11.6	11.5	11.3	11.1	10.9	10.7	10.4	10.2	10.0	9.8	9.6	9.4	9.2	9.1	8.9	8.8	8.7	8.6	8.5	8.4	8.2	8.1	7.9	
	10.4	10.2	10.1	9.9	9.7	9.6	9.4	9.2	9.0	8.9	8.7	8.5	8.3	8.2	8.0	7.9	7.7	7.5	7.4	7.2	7.1	6.9	6.8	6.7	6.5	6.4	6.2	6.1	6.0	5.8	
12月	7.8	7.6	7.4	7.2	7.0	6.8	6.6	6.4	6.3	6.1	5.9	5.8	5.7	5.5	5.4	5.3	5.2	5.1	5.1	5.0	4.9	4.8	4.7	4.6	4.6	4.5	4.4	4.3	4.2	4.1	4.1
	5.7	5.6	5.5	5.3	5.2	5.1	5.0	4.9	4.8	4.7	4.6	4.5	4.4	4.3	4.2	4.1	4.0	4.0	3.9	3.8	3.7	3.6	3.5	3.5	3.4	3.3	3.2	3.2	3.1	3.1	3.0

上段 = 日平均気温

下段 = 28日平均気温

(気象庁提供)

$8 \leq \theta$ S値 = 3 N/mm ²	
期間	3月19日～7月16日 9月6日～11月15日

$0 \leq \theta < 8$ S値 = 6 N/mm ²	
期間	11月16日～3月18日

暑中コンクリート 直近10年の平年値(10年)が 25℃を超える期間 S値 = 6N/mm ²	
期間	7月17日～9月5日

寒中コンクリート 打込み日を含む旬の日平均 気温が4℃以下の期間	
期間	1月1日～2月29日